



CORROSION PREVENTIVE COMPOUND – SOFT FILM

NATO CODE C-620 – MIL-PRF-16173 E Grade 2

DESCRIPTION

Nycoprotec 8132 is a solvent-dispersed corrosion preventive compound which deposits thin and easily removable soft film after evaporation of solvent.



APPLICATIONS

- Long term protection of ferrous and non-ferrous parts when exposed to indoor weather conditions, outdoor weather conditions with cover and during shipment
- Application by spraying or dipping

Characteristic	Unit	Typical Result	MIL-PRF-16173 Gr2 Limit	Test method
- Appearance	-	Hazy viscous liquid	-	visual examination
- Color	-	Brown	-	visual examination
- Density at 20°C	kg/dm ³	0.880	-	ASTM D 4052
- Flash point, PM	°C	40	min. 38	ASTM D 93
- Humidity (100%) cabinet corrosion test	h	960	min. 720	ASTM D 1748
- Salt spray (5%) corrosion test	H	>168	min 168	ASTM B 117
- Volatile Organic Content	g/L	340	max. 340	ASTM D 3960
- Non volatile content, 3h @ 110°C	%w	61	-	ASTM D 2369

The values above are typical values. They do not constitute any contractual commitment. Sales specifications are available on request. The present technical data sheet replaces all the previous editions.

